





AMF TOPIQ[®] Prime



- Excellent sound absorption (0.95 α_w)
- Excellent light reflectance (88%)
- ISO 5
- Ideal for offices, retail, classrooms, learning applications and underground garages





AMF TOPIQ® PRIME

KNAUF GEILING Solutions

Edge details	Board	Tegular 24/90		Tegula	ar 15/90			
Additional edge details on request								
Thickness (mm)	15	15		15	<u> </u>			
Dimensions (mm) Additional sizes on request	600 x 600 625 x 625 1200 x 600 1250 x 625	600 x 600 625 x 625 1200 x 600	600 x 600 625 x 625 1200 x 600					
System	Exposed demountable - System C	Exposed demountable - System C						
Weight Ko	2.4 kg / m²	2.4 kg / m ²						
Colour	White							
Sound absorption	EN ISO 354 α _w = 0.95 as per EN ISO 11654 Frequency f (Hz)	- Class A 125	250	500	1000	2000	4000	
	α _P NRC = 0.90 as per ASTM C 423	0.50	0.85	0.95	0.90	1.00	1.00	
Sound attenuation								
Sound reduction	EN ISO 10140-2 R _w = 13 dB as per EN ISO 717-1							
Fire reaction	Euroclass A1 as per EN 13501-1 Class A as per ASTM E 84							
Light reflectance	88%							
Humidity resistance	100% RH							
Clean room	ISO 5 as per EN ISO 14644-1	ISO 5 as per EN ISO 14644-1						
Indoor air quality	LIIT IIW EN 13964	ANT COME						
Cleanability	2							
Sustainability	исили и и Исили и исили и и	www.blauer-eng	el.de/uz132					

Products may vary from country to country. Please contact your local sales representative. For further information and legal notice, please visit our website.